

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

IN THE CLAIMS

Claim 1 (original): A method of fabricating a liquid crystal display panel, comprising the steps of:

preparing an upper substrate and a lower substrate;
bonding the upper substrate to the lower substrate;
cleaning exposed surfaces of the bonded upper and lower substrates; and
eliminating the exposed surfaces of the bonded upper and lower substrates.

A/ Claim 2 (original): The method according to claim 1, wherein the step of cleaning exposed surfaces includes dry-etching.

Claim 3 (original): The method according to claim 1, wherein the step of eliminating the exposed surfaces includes wet-etching.

Claim 4 (original): The method according to claim 1, further including the steps of:

forming a thin film transistor on the lower substrate;
forming a protective layer on the lower substrate; and
forming a pixel electrode on the protective layer to electrically contact the thin film transistor.

Claim 5 (currently amended): The method according to claim 4, wherein the pixel electrode is formed of a transparent conductive material including one of indium-tin-oxide (ITO), indium-zinc-oxide (IZO), and indium-tin-zinc-oxide (ITZO).

Cont'd
A1
Claim 6 (currently amended): The method according to claim 4, wherein the protective layer is formed of an organic insulating material including one of an acrylic organic compound, ~~Teflon~~⁷ TEFLON®, benzocyclobutene (BCB), ~~Cytop~~⁷ Cytop®, and perfluorocyclobutane (PFCB).

Claim 7 (original): The method according to claim 4, wherein the step of forming the thin film transistor includes:

forming a gate electrode on the lower substrate;

forming a gate insulating film on the lower substrate to cover the gate electrode;

forming an active layer on the gate insulating film; and

forming a source electrode and a drain electrode on the active layer.

Claim 8 (original): The method according to claim 7, wherein the source electrode and drain electrode contact the gate insulating film.

Claim 9 (currently amended): The method according to claim 7, wherein the pixel electrode contacts ~~parallel~~ flat and inclined surfaces of the drain electrode via a contact hole to expose the drain electrode.

Claim 10 (original): A method of fabricating a liquid crystal display panel, comprising the steps of:

- bonding an upper substrate to a lower substrate;
cleaning exposed surfaces of the bonded upper and lower substrates; and
removing the exposed surfaces of the bonded upper and lower substrates.

Claim 11 (original): The method according to claim 10, wherein the step of cleaning exposed surfaces includes dry-etching.

Claim 12 (original): The method according to claim 10, wherein the step of removing the exposed surfaces includes wet-etching.

Claim 13 (original): The method according to claim 10, wherein the step of removing the exposed surfaces uniformly reduces a thickness of the liquid crystal display panel.

Claim 14 (original): A method of fabricating a liquid crystal display panel, comprising the steps of:

forming a gate electrode on a lower substrate;

forming a gate insulating film on the lower substrate to cover the gate

electrode;

forming an active layer on the gate insulating film; and

forming a source electrode and a drain electrode on the active layer;

bonding an upper substrate to the lower substrate;

cleaning exposed surfaces of the bonded upper and lower substrates; and

removing the exposed surfaces of the bonded upper and lower substrates.

Claim 15. (original): The method according to claim 14, wherein the step of cleaning exposed surfaces includes dry-etching.

Claim 16 (original): The method according to claim 14, wherein the step of removing the exposed surfaces includes wet-etching.

Claim 17 (original): The method according to claim 14, further including the steps of

forming a protective layer on the lower substrate; and

forming a pixel electrode on the protective layer to electrically contact the drain

electrode.

Claim 18 (currently amended): The method according to claim 17, wherein the pixel electrode is formed of a transparent conductive material including one of indium-tin-oxide (ITO), indium-zinc-oxide (IZO), and indium-tin-zinc-oxide (ITZO).

Cont'd
A1
Claim 19 (currently amended): The method according to claim 17, wherein the protective layer is formed of an organic insulating material including one of an acrylic organic compound, ~~Teflon~~⁷ TEFLON®, benzocyclobutene (BCB), ~~Cytop~~⁷ CYTOP®, and perfluorocyclobutane (PFCB).

Claim 20 (original): The method according to claim 14, wherein the step of removing the exposed surfaces uniformly reduces a thickness of the liquid crystal display panel.

Claim 21 (new): The method according to claim 1, wherein the step of eliminating the exposed surfaces of the bonded upper and lower substrates uniformly reduces a thickness of the liquid crystal panel.
